



The extreme strange metal YbRh_2Si_2

Silke Paschen

Institute of Solid State Physics, TU Wien




Strange metal behaviour in SCES



(Taupin & SP, Crystals 12 (2022) 251)


$$\rho = \rho_0 + A'T$$

Planckian dissipation?



$$\rho = \rho_0 + \rho_{\text{in}} = \rho_0 + A'T = \rho_0 + \frac{m}{ne^2} \frac{1}{\tau} = \rho_0 + \frac{m}{ne^2} \alpha \frac{k_B T}{\hbar} \quad \text{Drude model with } \frac{1}{\tau} \sim T$$

Motivations to understand strange metal behaviour in SCES




(Taupin & SP, Crystals 12 (2022) 251)


Non-Fermi liquid states of interest in their own right
 p and x tuned strange metals have a superconducting dome

Superconducting domes in SCES


The cuprate $\text{YBaCuO}_{6-\delta}$




The iron pnictide FeSe



The fulleride compound C_{60}





Magic angle twisted bilayer graphene




(SP & Si, Nat. Rev. Phys. 3 (2021) 9, and refs. therein)

Superconducting domes in heavy fermion metals


CeCu₂Si₂ (Yuan et al., Science 2003) **CePd₂Si₂ (Mathur et al., Nature 1998)**




CeRhIn₅ (Yashima, PRB 2007)




CeCoIn₅ (Knebel, C. R. Phys. 2011 & refs.)



Quantum critical point scenario: Entropy accumulation




(Taupin & SP, Crystals 12 (2022) 251)



(SP & Si, Nat. Rev. Phys. 3 (2021) 9)

YbRh₂Si₂: A model quantum critical heavy fermion metal



(Custers et al., Nature **424** (2003) 524)

Heavy Fermi liquids

$$\rho = \rho_0 + AT^2$$

$$C/T = \gamma$$

$$A \sim (m^*)^2$$

$$\gamma \sim m^*$$


$$m^* = m(1 + \frac{1}{3}F_1^S)$$

With orbital degeneracy:




$$\tilde{A} = \frac{A}{\frac{1}{2}N(N-1)}$$

$$\tilde{\gamma} = \frac{\gamma}{\frac{1}{2}N(N-1)}$$

(Tsuji et al., Phys. Rev. Lett. 94 (2005) 057201) →






Discontinuities appear upon tuning: FL parameters diverge




(SP & Si, Nat. Rev. Phys. 3 (2021) 9, and refs. therein)

Discontinuities appear upon tuning: FL parameters diverge





(Nat. Rev. Phys. 3 (2021) 9; Paglione et al., Phys. Rev. Lett. 24 (2003) 246405)

YbRh₂Si₂: A model quantum critical heavy fermion metal



“Normal” QCPs follow Ginzburg, Landau, Wilson paradigm

Predictions for electrical resistivity



No linear resistivity

$x = 0$: clean limit

$x > 1$: dirty limit

(Rosch, Phys. Rev. Lett. 82 (1999) 4280)

“Normal” QCPs follow Ginzburg, Landau, Wilson paradigm

Predictions for some thermodynamic properties

	$d = 2$	$d = 3$	$d = 2$	$d = 3$
	$z = 2$	$z = 2$	$z = 3$	$z = 3$
$\alpha_{\text{cr}} \sim$	$\ln \ln \frac{1}{T}$	$T^{1/2}$	$\ln \frac{1}{T}$	$T^{1/3}$
$C_{\text{cr}} \sim$	$T \ln \frac{1}{T}$	$-T^{3/2}$	$T^{2/3}$	$T \ln \frac{1}{T}$
$\Gamma_{r,\text{cr}} \sim$	$\frac{\ln \ln \frac{1}{T}}{T \ln \frac{1}{T}}$	$-T^{-1}$	$T^{-2/3} \ln \frac{1}{T}$	$\left(T^{2/3} \ln \frac{1}{T}\right)^{-1}$


d : dimension, $z = 2$: AFM metal, $z = 3$: FM metal

α : thermal expansion, C : specific heat, $\Gamma = \alpha/C$: Grüneisen ratio

No hyperscaling above the upper critical dimension



(v. Löhneysen et al., Rev. Mod. Phys. 79 (2007) 1015; Hertz & Millis)

Evolution of Hall effect across the QCP: YbRh_2Si_2






(SP et al., Nature 432 (2004) 881) ↑

(Friedemann et al., PNAS 107 (2010) 14547) →






Relation of Hall crossover and NFL behavior in $\rho(T)$





(Custers et al., Nature 424 (2003) 524) \uparrow
 (Friedemann et al., PNAS 107 (2010) 14547) \rightarrow

Kondo destruction QCP scenario



(SP & Si, Nat. Rev. Phys. 3 (2021) 9) \uparrow
 (Friedemann et al., PNAS 107 (2010) 14547) \rightarrow



Kondo destruction QCP scenario



(SP & Si, Nat. Rev. Phys. 3 (2021) 9) \uparrow

(Coleman et al., JPCM 13 (2001) R723; Schröder et al., Nature 407 (2000) 351)

Kondo destruction QCP scenario




(SP & Si, Nat. Rev. Phys. 3 (2021) 9) \uparrow


(Coleman et al., JPCM 13 (2001) R723; Shishido et al, JPSJ 74 (2005) 1103)

Dynamical response: THz time-domain transmission spectroscopy


- Real and imag. part of $\sigma(\omega)$
- No Kramers-Kronig transformation
- Thin films needed!



Molecular beam epitaxy system





HAADF-STEM image



(Prochaska et al., Science 367 (2020) 285)


Dynamical scaling in quantum critical YbRh_2Si_2

THz time-domain transmission spectroscopy on MBE films of YbRh_2Si_2



(Prochaska et al., Science 367 (2020) 285)

Relation to the high- T_C cuprates: Strange metal behavior





(Takagi et al., Phys. Rev. Lett. 69 (1992) 2975)

Relation to the high- T_c cuprates: Carrier (de)localization

Phase diagram at 50 T


Change of carrier concentration



(Badoux et al., Nature 531 (2016) 210)

Relation to the high- T_C cuprates: Dynamical scaling in $\sigma(\omega)$





Optical conductivity of optimally doped $\text{Bi}_{2.23}\text{Sr}_{1.9}\text{Ca}_{0.96}\text{Cu}_2\text{O}_{8+\delta}$



(van der Marel et al., Nature 425 (2003) 271)


(Carbone et al., PNAS 2008)↑

Carrier (de)localization in other SCES?




(Taupin & SP, Crystals 12 (2022) 251)

Planckian dissipation in electrical transport?




(Taupin & SP, Crystals 12 (2022) 251)

Planckian dissipation in electrical transport?



(Taupin & SP, Crystals 12 (2022) 251)

Planckian dissipation in optical conductivity?




(Li, Kono, Si & SP, arXiv:2205.13382)

Planckian dissipation in optical conductivity?


$$\text{Re}[\sigma(\omega)] = \sigma_1 = \frac{ne^2\tau}{m} \frac{1}{1 + \omega^2\tau^2}$$

$$\text{Im}[\sigma(\omega)] = \sigma_2 = \frac{ne^2\tau}{m} \frac{\omega\tau}{1 + \omega^2\tau^2}$$

Pb at room temperature




Al at room temperature



(Li, Kono, Si & SP, arXiv:2205.13382)

Planckian dissipation in optical conductivity?



YbRh₂Si₂: highly non-Drude behavior in strange metal regime



(Li, Kono, Si & SP, arXiv:2205.13382)



Is there superconductivity at the QCP of YbRh_2Si_2 ?

Generic phase diagram of the cuprates Phase diagram of YbRh_2Si_2




(Proust et al., PNAS 113 (2016) 13654) (Custers et al., Nature 424 (2003) 524)

The Vienna Microkelvin Laboratory




www.EMPlatform.eu

Electrical resistivity at ultralow temperatures: Iso- B curves



(Nguyen et al., Nat. Commun. 12 (2021) 4341)


Electrical resistivity at ultralow temperatures: Iso- T curves




(Nguyen et al., Nat. Commun. 12 (2021) 4341)

Temperature–magnetic field phase diagrams

YbRh_2Si_2



$^{174}\text{YbRh}_2\text{Si}_2$






Orbital-limiting fields: 24 mT (5 mT)

Pauli-limiting fields: 15 mT (6.4 mT)


(Nguyen et al., Nat. Commun. 12 (2021) 4341)

Magnetic field effect on “dome” structure




Linear-in- T electrical resistivity down to T_C at QCP

YbRh₂Si₂




YbRh₂Si₂ (earlier batch)



(Nguyen et al., Nat. Commun. 12 (2021) 4341)

(Trovarelli et al., Phys. Rev. Lett. 85 (2000) 626)


YbRh_2Si_2 : An extreme strange metal (3.5 order of magnitude)



(Nguyen et al., Nat. Commun. 12 (2021) 4341)


Advance understanding by connecting the various platforms!

Generic phase diagram of the cuprates



(Proust et al., PNAS 113 (2016) 13654)

Phase diagram of YbRh_2Si_2



(Refs. in this talk)

S. Dzsaber*, G. Eguchi, J. Larrea J.*, **D. C. MacFarland***, V. Martelli*, **D. H. Nguyen**,
L. Prochaska, A. Prokofiev, **A. Sidorenko***, R. Svagera, **M. Taupin**, M. Waas, X. Yan,
D. A. Zocco; **A. M. Andrews**, H. Detz, W. Schrenk, G. Strasser; M. Bonta, A. Limbeck; P. Blaha
Vienna University of Technology, Austria

A. Cai*, H.-H. Lai*, S. Grefe, K. Ingersent*, C.-C. Liu, E. M. Nica*, R. Yu*, **Q. Si**
X. Li, J. Kono

E. Bianco, S. Yazdi, E. Ringe
Rice University, USA

G. Knebel, G. Lapertot
Université Grenoble Alpes, CEA, Grenoble INP, IRIG, PHELIQS, Grenoble, France

E. Schuberth
Technische Universität München, Germany

T. Shiroka; A. McCollam, L. M. K. Tang, B. Vlaar; F. Weickert, R. McDonald, L. Winter,
M. Jaime

Paul Scherrer Institut, High Field Magnet Laboratory Nijmegen, Los Alamos National Laboratory

O. Rubel

Department of Materials Science and Engineering, McMaster University

